

Polyisoprene (IR)	Tg	Viscosity Mooney ML (1+4) 100°C
ISOG RIP (60% 3,4 - IR)	-11°C	70
