

High Cis Grades	Cis (%)	Viscosity ML (1+4) 100°C
Europrene® NEOCIS BR 40	97	43
Europrene® NEOCIS BR 60	97	63